# HED<sup>®</sup> Specification

Title: Supplier Paint Aesthetic Specification	Number: PS225001	Approved By:	Tom Szewczyk	
--	------------------	--------------	--------------	--

## 1.0 Purpose

1.1 To outline the minimum aesthetic criteria for supplier painted products.

### 2.0 Scope

- 2.1 All powder coated aluminum enclosures endplates, or brackets
- 2.2 Does not apply to internal module applications and non-exposed surfaces

## 3.0 Quality Level of Defect/By Area

- 3.1 Dirt
  - Allowed as long as paint adhesion is not affected.
- 3.2 Craters
  - Allowed if not through to substrate or bare surface.
- 3.3 Sags and Runs
  - Very slight sag that is difficult to notice is allowed, only on face surfaces and <u>not</u> on gasket mating surfaces.
- 3.4 Substrate Scratches (Scratches to substrate only. Paint/Coating over substrate scratches.)
  - Allowed if not visible when viewed for 3 seconds at a nominal distance of 24 inches.
    - Allowed as long as paint adhesion and function of the part is not affected.
- 3.5 Overspray/Dry spray
  - Allowed
- 3.6 Paint Coverage (Thickness)
  - Full coverage required on all exterior surfaces.
- 3.7 Paint Build-up on Tapped Holes (from plugs)
  - Allowed up to a maximum height of .007" from dry spray.
- 3.8 Orange Peel
  - Light orange peel is allowed (Orange peel is allowed as long as it does not affect functioning of gasket mating surfaces).
- 3.9 Solvent Popping
  - Allowed if light pinhole-type solvent pops which are visible only when viewed at an angle. No clusters, only small random pops not visible when viewed for 3 seconds at a nominal distance of 24 inches.
    Allowed if not through to substrate or bare surface.
- 3.10 Scratches to Painted/Coated Surface (No substrate scratches or defects)
  - Allowed if not through to substrate or bare surface and if not visible when viewed for 3 seconds at a nominal distance of 24 inches.
  - Allowed as long as paint adhesion and functioning of the part is not affected.
- 3.11 Substrate/Surface Discontinuities
  - Non-uniform surface appearances such as streaks, die lines, stains, carbon marks, or discoloration are allowed if not visible when viewed for 3 seconds at a nominal distance of 24 inches.
  - Allowed as long as paint adhesion and functioning of the part is not affected.

#### 4.0 Revision History

Rev.	Date	Sections Affected / Description
Rev.	Dale	Sections Affected / Description
А	10/04/07	Initial Release
В	12/15/08	Reviewed and approved by PSV Manager. Corrected footer and header, and added Revision
		History. No changes made to document contents.
С	07/31/12	Changed scope from "All painted metal enclosures or brackets" to "All powder coated aluminum enclosures endplates, or brackets" and "Does not apply to internal module applications and non-exposed surfaces". Added "Paint Build-up on Tapped Holes (from plugs) – Allowed up to a maximum height of .007" from dry spray."